

BOTH SIDES SMOOTH WHITE CORE PASTEBOARD  
CARTONCINO BIANCO, INTERNO BIANCO

GSM	THICKNESS	BULK	TABER STIFFNESS 7,5°	
Grammatura	Spessore	Volume	Rigidità Taber 7,5°	
			Longitudinal	Transversal
g/mq	mm	cm <sup>3</sup>	MD	CD
1100	1,5	1,39	4800	1850
1330	2	1,45	6850	3150

## TOLERANCES

### Tolleranze

GSM	+/- 5%
MOISTURE 6,5%	+/- 1%
THICKNESS	+/- 5%
STIFFNESS	+/- 10%